WL-TR-96-4049



PUBLISHED NONLINEAR OPTICAL USES OF ZINC GERMANIUM DIPHOSPHIDE

NILS C FERNELIUS

APRIL 1996

FINAL REPORT FOR 09/01/92--02/29/96

Approved for public release; distribution unlimited

DTIC QUALITY INSPECTED 4

MATERIALS DIRECTORATE
WRIGHT LABORATORY
AIR FORCE MATERIEL COMMAND
WRIGHT-PATTERSON AIR FORCE BASE, OH 45433-773

19960705 090

NOTICE

WHEN GOVERNMENT DRAWINGS, SPECIFICATIONS, OR OTHER DATA ARE USED FOR ANY PURPOSE OTHER THAN IN CONNECTION WITH A DEFINITELY GOVERNMENT-RELATED PROCUREMENT, THE UNITED STATES GOVERNMENT INCURS NO RESPONS-IBILITY OR ANY OBLIGATION WHATSOEVER. THE FACT THAT THE GOVERNMENT MAY HAVE FORMULATED OR IN ANY WAY SUPPLIED THE SAID DRAWINGS, SPECIFICATIONS, OR OTHER DATA, IS NOT TO BE REGARDED BY IMPLICATION, OR OTHERWISE IN ANY MANNER CONSTRUED, AS LICENSING THE HOLDER, OR ANY OTHER PERSON OR CORPORATION; OR AS CONVEYING ANY RIGHTS OR PERMISSION TO MANUFACTURE, USE, OR SELL ANY PATENTED INVENTION THAT MAY IN ANY WAY BE RELATED THERETO.

THIS REPORT IS RELEASABLE TO THE NATIONAL TECHNICAL INFORMATION SERVICE (NTIS). AT NTIS, IT WILL BE AVAILABLE TO THE GENERAL PUBLIC, INCLUDING FOREIGN NATIONS.

THIS TECHNICAL REPORT HAS BEEN REVIEWED AND IS APPROVED FOR PUBLICATION.

NILS C. FERNELIUS, Project Engineer Electronic & Optical Mat'ls Branch

Electromagnetic Mat'ls & Surv. Div.

ROBERT L. DENISON, Chief

Electronic & Optical Mat'ls Branch Electromagnetic Mat'ls & Surv. Div.

WILLIAM R. WOODY, Chief Electromagnetic Mat'ls & Surv. Div.

Materials Directorate

IF YOUR ADDRESS HAS CHANGED, IF YOU WISH TO BE REMOVED FROM OUR MAILING LIST, OR IF THE ADDRESSEE IS NO LONGER EMPLOYED BY YOUR ORGANIZATION PLEASE NOTIFY <u>WL/MLPO</u>, BLDG 651, 3005 P ST STE 6, WPAFB OH 45433-7707, TO HELP MAINTAIN A CURRENT MAILING LIST.

COPIES OF THIS REPORT SHOULD NOT BE RETURNED UNLESS RETURN IS REQUIRED BY SECURITY CONSIDERATIONS, CONTRACTUAL OBLIGATIONS, OR NOTICE ON A SPECIFIC DOCUMENT.

REPORT DOCUMENTATION PAGE

Form Approved
OMB No. 0704-0188

Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden. to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188), Washington, DC 20503.

1.	AGENCY USE ONLY (Leave blank)	2. REPORT DATE APR 96	3. REPORT TYPE AND final 09/01	D DATES COVERED /92 - 02/29/96		
4. TITLE AND SUBTITLE 5. FUNDING NUMBERS						
	PUBLISHED NONLINEAR OP	PE 61102				
ŀ	DIPHOSPHIDE			PR 2305		
_		TA FO				
6. A	LUTHOR(S)			WU FJ		
	NILS C. FERNELIUS					
7. P	ERFORMING ORGANIZATION NAM	E(S) AND ADDRESS(ES)		8. PERFORMING ORGANIZATION REPORT NUMBER		
	MATERIALS DIRECTORATE			NEI ON HOMBEN		
	WRIGHT LABORATORY			177 FD 06 4040		
	AIR FORCE MATERIEL COM			WL-TR-96-4049		
	WRIGHT PATTERSON AFB	ОН 45433-7734				
9 . S	PONSORING/MONITORING AGENC	Y NAME(S) AND ADDRESS(ES)		10. SPONSORING / MONITORING		
	MATERIALS DIRECTORATE			AGENCY REPORT NUMBER		
	WRIGHT LABORATORY					
	AIR FORCE MATERIEL COM			WL-TR-96-4049		
l II	WRIGHT PATTERSON AFB	он 45433-7734				
11.	SUPPLEMENTARY NOTES					
	. DISTRIBUTION / AVAILABILITY STA			12b. DISTRIBUTION CODE		
	APPROVED FOR PUBLIC RE	CLEASE; DISTRIBUTION	IS UNLIMITED.			
				·		
13.	ABSTRACT (Maximum 200 words)					
	This report gives caps	sule summaries of al	1 published work	using the nonlinear		
	optical properties of	zinc germanium diph	osphide (ZnGeP2)	. It is organized in		
	several groupings-earl	Ly American work, Ru	ssian, and recen	t western work. A		
	general bibliography	is given as an appen	alx.			
l						
l						
14.	SUBJECT TERMS			15. NUMBER OF PAGES		
	zinc germanium diphosp	34				
	generation (SHG) option frequency generation					
47		SECURITY CLASSIFICATION				
1/.	SECURITY CLASSIFICATION 18. OF REPORT	OF THIS PAGE	19. SECURITY CLASSIFIC OF ABSTRACT	CATION 20. LIMITATION OF ABSTRACT		
	UNCLASSIFIED	UNCLASSIFIED	UNCLASSIFIED	SAR		

TABLE OF CONTENTS

Section		Page
1	Introduction	1
2	Early American work	2
3	Russian use of ZnGeP2 in NLO	3
4	Summary of Russian work	18
5	Recent Western work in ZnGeP ₂	19
6	Appendix - Bibliography	23

PUBLISHED NONLINEAR OPTICAL USES OF ZINC GERMANIUM DIPHOSPHIDE

by Nils C. Fernelius

INTRODUCTION

Currently the crystal of choice for optical parametric oscillators (OPO) operating in the 3-5 μm atmospheric window range is zinc germanium diphosphide (ZGP). The OPO is usually pumped by a holmium laser operating around 2 μm . Several factors delayed the common usage of ZGP in nonlinear optical (NLO) devices. First there was the problem of obtaining crack free crystals. The other serious problem, still not completely resolved, is a native defect optical absorption shoulder on the short wavelength side of the transparency window which extends beyond 2 μm . This degrades high power operation when using a 2 μm pump.

The first NLO uses of ZGP were demonstrated at Bell Labs in 1971 as a result of the interaction of the NLO group with the ternary semiconductor group. Most of the work entailed sum and difference frequency generation (SFG) & (DFG) plus one second harmonic generation (SHG) paper. There were five papers by G.D. Boyd et al. in 1971-1972. The work was summarized in an Avionics Lab tech report by Nichols, Corbin and Donlan in 1974. Due to reorganizations, both civilian and military, work in the area ceased. For almost the next 20 years, all research on this material was done in the Soviet Union. In the last few years, NLO ZGP work in the West has been revived.

This work will try to summarize the literature in three categories: early American, Russian, and recent Western work. Each category consists of a list of papers, the affiliation of the authors and a capsule summary of the work. The following were grouped in the Russian section: the paper by Churnside et al. since it was performed on a crystal brought from Russia when Gribenyukov was on sabattical, some later work of Gopal Bhar even though it was performed in India, and the work of Vodopyanov after he started working at Imperial College, London.

Gopal Bhar did some significant work which does not fit in the above categories. Initially he published a number a papers obtaining Sellmeier equations by reanalyzing Boyd's data. From this he published a number of SHG and OPO tuning curves including temperature dependences. These papers will be listed in the general bibliography combining all categories.

EARLY AMERICAN WORK

A1 - G.D. Boyd, E. Buehler & F.G. Storz, Bell Telephone Laboratories, Murray Hill, New Jersey

Linear and nonlinear optical properties of ZnGeP $_2$ and CdSe Appl. Phys. Lett. **18** 301-304 (1971) measures n_o , n_e , dn_o/dT , dn_e/dT

shows three-frequency phase matching plots for $\theta_m = 90^{\circ}$, 74° , 66° , 60°

A2 - G.D. Boyd, W.B. Gandrud & E. Buehler, BTL

Phase-matched up conversion of 10.6-μ radiation in ZnGeP₂

Appl. Phys. Lett. **18** 446-448 (1971)

Sum frequency generation (SFG): 10.6 & 1.06 μ m Experimental: $\theta_m = 84^{\circ}$, $d\theta_m/dT = -0.007$ deg/°C crystal length = 1 cm

A3 - G.D. Boyd, T.J. Bridges, C.K.N. Patel & E. Buehler, BTL Phase-matched submillimeter wave generation by difference-frequency mixing in ZnGeP₂

Appl. Phys. Lett. **21** 553-555 (1972)
Difference frequency generation (DFG) using two step-tunable CO₂ lasers
Phase-matched outputs between 70 cm⁻¹ (143μm) and 110 cm⁻¹ (91μm)

A4 - Elgene R. Nichols, John C. Corbin, Jr. and Vincent L. Donlan
 Avionics & Materials Laboratories, Wright-Patterson AFB, Ohio

 A Review of Parametric Oscillators and Mixers and an Evaluation of Materials for 2-6µm Applications

Air Force Avionics Laboratory Tech Report

AFAL-TR-74-161, July, 1974 gain/watt 1cm long crystal vs output wavelength plots for pump wavelengths 1.06, 1.3, 1.83, and 2.1 μ m. pp.22-24 Optical parametric oscillator (OPO) performance for λ_{pump} = 1.06, 1.3 and 2.10 μ m.

A5 - J.L. Shay & J.H. Wernick Ternary Chalcopyrite Semiconductors: Growth, Electronic Properties, and Applications, Pergamon Press, Oxford, 1975

Chapter 6 - Noninear Optical Applications pp. 153-174

pp. 30-34

RUSSIAN USE OF ZnGeP2 IN NLO

R1 - N.P. Andreeva, S.A. Andreev, I.N. Matveev, S.M. Pshenichnikov & N.D. Ustinov Parametric conversion of infrared radiation in zinc germanium diphosphide Sov.J. Quantum Electron. 9 208-210 (1979)

Russian reference: Kvantovaya Elektron. (Moscow) 6 357-359 (1979)

Use as PARAMETRIC CONVERTER output @ 960 nm PUMP CHARACTERISTICS:

Nd:YAG (1.06 μ) τ = 30 ns power density = 3 MW/cm² rep rate = 12.5 Hz

Laser @ 3 MW/cm² no damage seen over 30 min

@ 20 MW/cm² damage after 5-10 pulses

 CO_2 Laser (10.6 μ) CW power ~ 1 W

@ 10 W/cm² no damage over 3-4 cycles of 30 min

CRYSTAL: single crystal ZnZGeP2 working faces polished

thickness 3 mm

 $\Theta_{pm} = 82.5^{\circ}$

 $\alpha(960 \text{nm}) = 10 \text{ cm}^{-1}$

 $\alpha(1.06 \,\mu) = 8 \,\text{cm}^{-1}$

 $\alpha(10.6 \,\mu) = 2 \, \text{cm}^{-1}$

R2 - Yu.M. Andreev, V.G. Voevodin, A.I. Gribenyukov, O.Ya. Zyryanov, I.I. Ippolitov, A.N. Morozov, A.V. Sosnin & G.S. Khmel'nitskii

Institute of Atmospheric Optics, Tomsk

Efficient generation of the second harmonic of tunable CO₂ laser radiation in ZnGeP₂ Sov. J. Quantum Electron. **14** 1021-1022 (1984)

Russian reference: Kvantovaya Elektron. (Moscow) 11,1511-1512 (August 1984)

SHG of CO₂

PUMP CHARACTERISTICS: CW and pulsed rep rate 1.5 kHz τ = 0.1-10 ms average power in TEM₀₀ was 0.5 - 5 W depending on transition

damage threshold 60-65 MW/cm² @ λ = 10.6 m

no damage observed for CW of 1 kW/cm²

best pulsed power conversion efficiency,5%, was @0.6kW pump

CRYSTAL: Bridgman mechanical & chemodynamic polishing no AR coatings

 $\alpha(2.5-12\mu)$ less than 0.1 cm⁻¹

in 8.5-9.45 μ and λ > 10.6 m have phonon absorption

cross section area $\sim 3 \text{ cm}^2$ $\Theta = 76^\circ$

R3 - Yu.M. Andreev, T.V. Vedernikova, A.A. Betin, V.G. Voevodin, A.I. Gribenyukov, O.Ya. Zyryanov, I.I. Ippolitov, V.I. Masychev, O.V. Mitropol'skii, V.P. Novikov, M.A. Novikov & A.V. Sosin Inst.Atmosph. Optics, Tomsk Conversion of CO_2 and CO laser radiations in a $ZnGeP_2$ crystal to the 2.3-3.1 μ spectral range Sov.J. Quantum Electron. **15** 1014-1015 (1985) Russian ref.: Kvantovaya Elektron. **12** 1535-1537 (July 1985)

4th harmonic of CO2 efficiency ~ 0.1 % should get to 20% (0.0025-0.010)% 2nd harmonic of CO

PUMP CHARACTERISTICS:

energy 200 mJ/pulse TEA CO₂ $\tau \sim 170 \text{ ns}$ first 2nd harmonic type I ee->o ZnGeP2 in oven efficiency ~ 2% energy 4 - 10 mJ

second 2nd harmonic crystal 5 mm $\Theta = 48^{\circ}54'$ $\phi = 0^{\circ}25'$ 4th harmonic at least 0.2 mJ efficiency ~ 0.1%

 $\alpha(2-12\mu) \sim 2 \text{ cm}^{-1}$

SH 2 µW strongest line 0.8W CO SHG output power 8.5 W

a(2.8u) ~2.8 cm⁻¹ a(5μ) ~3.8 cm⁻¹

CW CO @ 10 kW/cm² for 6 hours showed no sign of damage

R4 - K.L. Vodop'yanov, V.G. Voevodin, A.I. Gribenyukov, & L.A. Kulevskii Institute of General Physics, Moscow

Picosecond parametric superluminescence in the ZnGeP2 crystal Bulletin of the Academy of Sciences of the USSR, Physical Series 49 146-149 (1985)

Russian reference: Izvestiya Akademii Nauk SSSR, Seriya Fizicheskaya 49 569-572 (1985)

use as OPO

PUMP CHARACTERISTICS:

Erbium laser (2.94 μ m) train of 25 pulses, t = 80 ps, rep rate 1 Hz, total energy in train of 10-15 mJ

ZnGeP2 CRYSTAL:

single crystal by Bridgmen a did not exceed 0.2 cm⁻¹ for λ = 2.5-8.5 μ m in three-phonon absorption band (8.3-9.5 μm) $\alpha = 0.3 \text{ cm}^{-1} (I = 8.8 \ \mu)$ calculate o-ee and o-eo tuning curves experiment o-eo : $\Theta = 84.5^{\circ}-79.3^{\circ}$ covering $\lambda = 5.51-5.38 \& 6.29-6.46 \ \mu m$ Crystal 42 mm long cut at an angle of 64° max pump intensity 4 x 109 W cm⁻¹

R5 - L.I. Andreeva, K.L. Vodop'yanov, S.A. Kaidalov, Yu.M.Kalinin, M.E. Karasev, L.A. Institute of General Physics, Moscow Kulevskii & A.V. Lukashev Picosecond erbium-doped YAG laser (λ = 2.94 μ) with active mode locking Sov.J. Quantum Electron. 16 326-333 (1986)

Russian Ref.: Kvantovaya Elektron. 13 499-509 (March 1986)

use as OPO with ZnGeP2

PUMP CHARACTERISTICS: $Y_3Al_5O_{12}$:Er³⁺ λ = 2.94 μ m rep rate 1-1.5 Hz

generated train with energy 12 mJ of 25 pulses with energy 0.5 mJ

(+/-

3%) per spike and 40+/-10 ps duration at 4th harmonic

pulse separation 6.7 ns FWHM envelope 160 ns

optic axis to ⊥ at end surface was 84° CRYSTAL

the polar angle was $\varphi = 45^{\circ}$

o-eo interaction

signal $\lambda = 6.3 \, \mu \text{m}$

idler $\lambda = 5.5 \,\mu m$

R6 - V.E. Zuev, Yu.M. Andreev, V.G. Voevodin, A.I. Gribenyukov, V.A. Kapitanov, A.V. Sosnin, G.A. Stuchebrov, & G.S. Khelnitskii

Institute of Atmospheric Optics, Tomsk

Multifrequency dial sensing of the atmospheric gaseous constituents using the first and second harmonics of a tunable CO₂ laser radiation Proceedings 13th International Laser Radar Conference, Toronto, Canada 1986, NASA Conference Publication 2413 108-110 (1986)

SHG of CO₂

PUMP CHARACTERISTICS:

16 CO₂ wavelengths from R14 to R32

60 MW/cm² for 200 ns pulses

200 kW/cm² for CW

CRYSTAL: 10 x 20 mm cross section

3-10 mm thickness with polished ends

R7 - Yu.M. Andreev, V.G. Voevodin, A.I. Gribenyukov, & V.P. Novikov

Institute for Applied Physics, Gorki

Mixing of frequencies of CO2 and CO lasers in ZnGeP2 crystals

Sov.J. Quantum Electron. 17 748-749 (1987)

Russian ref: Kvantovaia Elektronika 14 1177-1178 (June, 1987)

Summed CO and CO₂

PUMPS: CO₂ 5.7 W

CO 4.7 W

CRYSTALS:

Length	$\Theta_{\rm pm}$ for	Azimuthal	Absorpti	on co	efficient	Damage	threshold
mm	normal				CO ₂ +CO		
	incidence	0	in cm ⁻¹			kW/d	cm ²
3.1	48	0	0.83	0.32	0.41	200	250
8.0	90	45	0.46	0.1	0.2		
	dan	nage threhole	d for pulse	ed CO	2 60 MW/	cm ² for	200 ns pulses

R8 - Yu.M. Andreev, A.D. Belykh, V.G. Voevodin, P.P. Geiko, A.I. Gribenyukov, V.A. Inst. Atmospheric Optics, Tomsk Gurashvili & S.V. Izyumov Doubling of the emission of CO lasers with an efficiency of 3 %.

Sov.J. Quantum Electron. 17 490-491 (1987)

Russian ref.: Kvantovaya Elektron. 14 782-783 (April1987)

SHG of CO

PUMP: CO Q-switched energy per pulse 2 mJ @ 10 Hz; 0.6 mJ @ 100 Hz 0.1 mJ @ 200 Hz

CRYSTAL 7 mm long Θ = 47°30' ϕ = 0 chemodynamic polish, no AR maximum external efficiency of whole SHG system 3.2%

R9 - Yu.M. Andreev, A.I. Gribenyukov, V.V. Zuev, N.V. Karlov, V.D. Karyshev, A.V. Kisletsov, I.O. Kovalev, A.V. Korablev, G.P. Kuz'min, L.A. Kulevskii & A.A. Nesterenko Institute of General Physics, Moscow

Second-harmonic generation in ZnGeP2 pumped by a continuously tunable CO2 laser Sov. Tech. Phys. Lett. **13** 595-596 (1987).

Russian ref.: Pis'ma v Zhurnal Tekhnicheskoi Fiziki 13 1423-1426 (12 Dec 1987)

SHG of CO₂

PUMP CHARACTERISTICS:

could tune CO₂ over 9.19-9.7 μ m & 10.15-10.8 μ m linearly polarized 15-70 mJ, pulse length FWHM $_{\sim}$ 50 ns achieved doubled tuning over 5.15-5.11, 4.80-4.73, 4.65-4.61 μ m CRYSTAL:

4.4 mm thick $\theta = 76^{\circ}$ $\Phi = 0^{\circ}$ $\alpha = 2.1$ cm⁻¹ spot 1.5 mm diameter, surface damage above 65 mJ or \sim 4 J/cm²

R10 - K.L. Vodop'yanov, V.G. Voevodin, A.I. Gribenyukov & L.A. Kulevskii High-efficiency picosecond parametric superradiance emitted by a ZnGeP2 crystal in the 5-6.3 μ range Inst. of General Physics, Moscow Sov.J. Quantum Electron. 17 1159-1161 (1987)

Russian ref: Kvantovaia Elektronika 14 1815-1819 (Sept. 1987)

OPO

PUMP CHARACTERISTICS:

 $Er^3+:Cr^3+:YSGG$ yttrium scandium gallium garnet λ = 2.79 μm τ = 150 ps +/- 25 rep rate 1 Hz up to 2 mJ/spike laser spot ~ 0.1 mm diameter (area = 0.00017 cm²)

CRYSTAL:

Bridgman α in range 2.8-8.3 μ did not exceed 0.1 cm⁻¹ no AR coatings Type II o->eo θ = 84° λ_1 = 5.96 μ m, λ_2 =5.25 μ m for I_p > 7.8 GW/cm² efficiency of conversion 16%

for $I_p = 16 \text{ GW/cm}^2$, efficiency 17.6% surface damage threshold 30 GW/cm²

vary θ 76-90°, output 5-5.3, 5.9-6.3 μm with quantum efficiency 17%, output power ~1 MW

R11 - Yu.M. Andreev, V.G. Voevodin, P.P. Geiko, A.I. Gribenyukov, V.V. Zuev, A.S. Solodukhin, S.A. Trushin, V.V. Churakov & S.F. Shubin

Inst.Atmospheric Optics, Tomsk
Transformation of the frequencies of nontraditional (4.3 and 10.4 µm) CO2 laser radiation bands in ZnGeP2 Sov.J. Quantum Electron. 17 1362-3 (1987)
Russian Russian ref: Kvantovaia Elektronika 14 2137-2138 (Nov. 1987)

SHG 4.3 µm + SFG with 10.4 µm PUMP CHARACTERISTICS:

average power of 4.3µm band did not exceed 10 mW

CRYSTAL: ŽnGeP₂ Type I interactions 7-13 mm thick

cut at angles $\theta = 53 \& 48.5^{\circ} \phi = 0$

best results from crystal 7mm length with θ = 47°30' and ϕ = 0 AR coating gave transmission up to 87.5% @ I = 4.3 μ ; 73% @ 10.4 μ measured SH phase-matching angle 55°50'

R12 - Yu.M. Andreev, V.Yu. Baranov, V.G. Voevodin, P.P. Geiko, A.I. Gribenyukov, S.V. Izyumov, S.M. Kozochin, V.D. Pis'mennyi, Yu.A. Satov & A.P. Strel'tsov I.V.Kurchatov Institute of Atomic Energy, Moscow

Efficient generation of the second harmonic of a nanosecond CO₂ laser radiation pulse Sov.J.Quantum Electron. **17** 1435-1436 (1987)

Russian Ref.: Kvantovaya Elektronika 14 2252- 2254 (Nov. 1987)

SHG of CO2

PUMP CHARACTERISTICS: CO₂ 2 ns pulse 9.52 μm

CRYSTAL: type I conversion

second harmonic generator: $\Theta = 76^{\circ}$, $\varphi = 0$ length 3 mm

fourth harmonic generator: $\Theta = 47^{\circ}$, $\varphi = 0$ length 10 mm both

crystals chemodynamic polished, no AR coating

 α did not exceed 0.1 cm $^{-1}$ from 2.5-8 μm

calculation showed that that length of 3mm optimal for 1 GW/cm²

damage threshold for fresh surface 2.5 J/cm²

R13 - Yu.M. Andreev, P.P. Geiko, V.V. Zuev, V.E. Zuev, O.A. Romanovskii, & S.F. Shubin Inst. Atmospheric Optics, Tomsk Advances in Gas-Analyzers Based on IR Molecular Lasers

Laser & Optical Remote Sensing: Instrumentation & Techniques, 28 Sept.- 1 Oct. 1987, North Falmouth, MA pp 152-155

SHG & sum frequency addition of CO_2 lines can cover much of the 2-5 and 8-12 μm part of the spectrum

R14 - Yu.M. Andreev, V.G. Voevodin, P.P. Geiko, A.I. Gribenyukov, V.V. Zuev, V.E. Zuev institute of Atmospheric Optics, Tomsk, USSR Effective source of coherent radiation based on CO2 lasers and ZnGeP2 frequency converters Laser & Optical Remote Sensing: Instrumentation & Techniques, 28 Sept.- 1 Oct. 1987 North Falmouth, MA, Optical Society of America 1987 Technical Digest Series, Vol. 18, pp. 300-303

SHG, FHG, SFG with CO₂ & CO chart of parameters of frequency converters

Cilait	or param	,		
	Laser	λinμm	W/cm2	τins
SHG	CO_2	9.23	10 ⁹	2 10-9
0110	CO ₂	10µm band	10 ⁹	2 10-9
	SH CO ₂	· ·	0.3 10 ⁹	2 10-9
	CO ₂	9.210.8	6 10 ⁷	1.72 10 ⁻⁷
	CO ₂	9.210.8	0.51 10 ⁶	10 ⁻⁴ 10 ⁻²
	CO ₂	4.3 µm band	-	1.53.3 10 ⁻⁷
	CO ₂	9.210.8	2 10 ⁵	CW
	CO	5.36.1	-	4.5 10 ⁻⁵
	CO	5.36.1	2.5 10 ⁵	CW
FHG	CO ₂	9.23	1 & 0.3 10 ⁹	2 10 ⁻⁹
THO	CO ₂	9.210.6	6 10 ⁷	1.72 10 ⁻⁷
SFG	CO2	4.3 & 10.4	•	1.53 10 ⁻⁷ & 6 10 ⁻⁷
SFG		5.36.1 &	2 10 ⁵	
	CO2	9.210.8		
			10 ⁶	5 10 ⁻⁵
	UU:UU2	2 5.36.1 &	10	
		9.210.6		

CRYSTAL: boules 20-25 mm diameter X 150 mm length crystal lengths, 3 mm, 7 - 10.5 mm.

R15. - Yu.M. Andreev, V.G. Voevodin, A.I. Gribenyukov, V.N. Davydov, V.I. Zhuravlev,

V.A. Kapitanov, T.D. Lezina, G.A. Struchebrov, and G.S. Khmel'nitskii

Inst. Atmospheric Optics, Tomsk

Beam-path gas analyzer based on a tunable CO2 laser with frequency doubling

J. Applied Spectroscopy 47(1) 662-666 (Jan. 1988)

Russian ref.: Zhurnal Prikladnoi Spektroskopii 47(1) 15-20 (July, 1987)

SHG with CO2

CO₂ LASER: Tuning range 9.2-10.8 μm

Maximum power 50 W Pulse rep rate up to 1500 Hz Pulse duration 0.1-10 msec

CRYSTAL: Size 3.6 x 10 X 20 mm

Working temperature of crystal 20-160 °C Wavelength range of SHG 4.6-5.4 µm

Inst. Atmospheric Optics, Tomsk R16 - V.E. Zuev

Spectroscopic studies of laser sounding of the atmosphere

International Laser Radar Conference, Innichen-San Candido, Italy, 20-24 June 1988 pp.119-121

describes system where ZGP is used as OPO, SHG, & SFG with CO2 & CO pumps

CRYSTAL: sizes up to 20-25 mm diameter & up to 150 mm length

R17 - Yu.M. Andreev, P.P. Geiko, V.V. Zuev, O.A. Romanovskii & S.F. Shubin Inst. Atmospheric Optics, Tomsk

Control of gas pollution of air medium with the aid of CO₂ and CO lasers equipped with frequency converters

XIII International Conference on Coherent & Nonlinear Optics, Minsk, 6-9 Sept 1988, Part II, Sections IX-XVI, pp. 221-222

SHG & SFG of CO2

LASER:

rep rate 100Hz

pulse length 100 ms Peak power 150 W

peak power of second harmonic 10 mW

R18 - Yu.M. Andreev, P.P. Geiko & V.V. Zuev

High-efficiency frequency conversion of IR lasers with ZnGeP₂ and CdGeAs₂ IAO, Tomsk

Advances in Laser Science III. Third International Laser Science Conference Atlantic City, NJ 1-4 Nov. 1987 AIP Conference Proceedings 172 190-2 (1988), eds. Andrew C. Tam, James L. Gole & William C. Stwalley Results on ZnGeP₂

FC type	Laser	λ in μm	τ in s
SHG	CO2	9.28	2 10-9
	SH CO2	4.64	1.5 10-9
	CO2	9.2-10.8	2 10-7
	CO	5.3-6.1	4 10-5
	CO	4.3	3.3 10-7
FHG	CO2	9.28	2 10-9
SFG	CO2	4.3	3 10-7
		10.4	6 10-7
	CO &	5.3-6.1	CW
	CO2	10.6	CW

CRYSTAL: boules 20-25 mm diameter, up to 150 mm length

R19 - Yu.M. Andreev, P.P. Geiko, V.V. Zuev, O.A. Romanovskii IAO, Tomsk Gas Analysis Using CO₂ Laser Frequency Converters

Advances in Laser Science III. Third International Laser Science Conference Atlantic City,NJ 1-4 Nov. 1987 AIP Conference Proceedings 172 193-5 (1988), eds. Andrew C. Tam, James L. Gole & William C. Stwalley

SHG & SFG of CO₂ & CO lasers using ZGP & TAS frequency doubled 10.3 µm by heating ZGP above 100°C

R20 - V.E. Zuev, M.V. Kabanov, Yu.M. Andreev, V.G. Voevodin, P.P. Geiko, A.I. Gribenyukov, V.V. Zuev Atmospheric Optics Inst., Tomsk Applications of efficient parametric IR-laser frequency converters Bull. Academy Sci., USSR, Physical Sciences 52 87-92 (1988)

Russian ref.: Izvestiya Akademii Nauk SSSR, Seriya Fizicheskaya **52**(6) 1142-1148 (1988)

plot of efficiency vs. crystal length

CRYSTALS: 20-25 mm diameter X up to 150 mm long

Results for ZnGeP₂ crystal

Form	Laser	λ in μm	τ in sec
SHG	CO_2	9.28	2 10-9
	CO_2	10.2-10.3	
	SH CO ₂	4.64	1.5 10 ⁻⁹
	CO ₂	9.2-10.8	2 10 ⁻⁷
	CO	5.3-6.1	4 10 ⁻⁵
	CO_2	4.3	3.3 10-7
FHG	CO_2	9.28	2 10-9
SFG	CO_2	4.3	3 10 ⁻⁹
		10.4	6 10 ⁻⁷
	CO &	4.3	3 10-7
	CO_2	10.4	6 10 ⁻⁷

R21 - G.C. Bhar, S. Das, U. Chatterjee, & K.L. Vodopyanov Burdwan U., India & Gen.Phys. Inst., Moscow

Temperature-tunable second-harmonic generation in zinc germanium diphosphide Appl.Phys.Lett. **54** 313-314 (1989)

SHG of CO₂ CRYSTAL:

 $\alpha(3-8\mu m)$ less than 0.2 cm⁻¹ size 2.5 cm diameter,15 cm length type I phase match with 48° cut 9.18-9.6 μ m doubled varying phase match angle and temperature

R22 - Yu.M. Andreev, A.N. Bykanov, A.I. Gribenyukov, V.V. Zuev, V.D. Karyshev, A.V. Kisletsov, I.O. Kovalev, V.I. Konov, G.P. Kuz'min, A.A. Nesterenko, A.E. Osorgin, Yu.M. Starodumov & N.I. Chapliev Inst.General Physics, Moscow Conversion of pulsed laser radiation from the 9.3-9.6 mm range to the second harmonic in ZnGeP₂ crystals

Sov. J. Quantum Electron. 20 410-414 (1990)

Russian Ref.: Kvantovaya Elektron. 17 476-480 (April 1990)

SHG of CO₂

PUMP CHARACTERISTICS: pulsed TEA CO₂ tunable 9.2-9.8 μm 110-120 ns spike with 1-1.1 μs low intensity tail

CRYSTAL:

length	λ	$\Theta_{\sf pm}$	α		1.4x1.4 cm
mm	μm	•	cm ⁻¹	cross	section
4.6	9.3	64.4	0.8-3.0		
4.0	9.3	62.7	0.6-1.2		
	9.6	64.9			

best Russian crystals had $\alpha(9\mu)$ = 0.5-0.4 cm⁻¹; $\alpha(4.5\mu)$ = 0.1-0.2

cm⁻¹

paper includes plots of efficiency vs. a, energy, energy density also plot of phase matching angle vs. temperature

R23 - K.L. Vodopyanov, L.A. Kulevskii, V.G. Voevodin, A.I. Gribenyukov, K.R. Allakhverdiev, & T.A. Kerimov General Physics Inst., Moscow High efficiency middle IR parametric superradiance in ZnGeP2 and GaSe crystals pumped by an erbium laser

Optics Communications **83** 322-326 (1991)

OPO

PUMP CHARACTERISTICS:

Er³+:YAG, λ = 2.94 μ τ = 110 ps ±10, 0.5-2 mJ, rep rate 1.2 Hz Er³+:YSGG, λ = 2.79 μ

CRYSTALS:

Type I (o-ee)

Type II (o-eo)

Crystal orientation

 $\Theta = 47^{\circ}, \varphi = 0$

 $\Theta = 84^{\circ}, \ \phi = 31^{\circ} (45^{\circ} \text{optimal})$

Range of ⊕ variation

47-49.550

76-90°

Tuning range achieved

4-10 μ 11 mm 5.2-5.6, 6.2-6.7 μ 42 mm

Crystal length Damage threshold

6.5 GW/cm²

30 GW/cm²

R24 - Yu.M. Andreev, P.P. Geiko & G.M. Krekov Tomsk Medicine Institute, Tomsk
 O.A. Romanovskii Inst. Atmosheric Optics, Tomsk
 Detection of trace concentration of some simple pollutants in Tomsk
 SPIE Vol. 1811 High-Resolution Molecular Spectroscopy pp. 367-370 (1991)

SHG, SFG of CO₂ also

also THG using TAS

R25 - K.L. Vodopyanov, L.A. Kulevskii, A.I. Gribenyukov, and K.R. Allakhverdiev General Physics Inst., Moscow

High efficiency middle IR parametric superradiance in ZnGeP₂ and GaSe crystals pumped by an erbium laser

Journal de Physique IV: Colloque 7, supplement au Journal de Physique III, Vol. 1, Decembre 1991 pp. C7-391 - C7-394 same as R23?

R26 - A.A. Betin, V.G. Voevodin, K.V. Ergakov, A.V. Kirsanov & V.P. Novikov Inst. Applied Physics, Siberian Polytechnical Inst., Tomsk Generator of infrared radiation at the second-harmonic frequency of a TEA CO₂ laser Sov.J. Quantum Electron. 21 735-738 (1991) Russian Ref.: Kvantovaya Elektron. 18 812-816 (July 1991)

SHG of CO2

PUMP CHARACTERISTICS: TEA CO₂ short peak 170-200 ns + μs tail maximum energy per pulse 3J

CRYSTAL: $\alpha(CO_2) = 0.3-2 \text{ cm}^{-1}$

max breakdown threshold after mechanical polish + surface treatment 60-80 MW/cm²(10-15 J/cm²);

after chemodynamic polish 40-60 MW/cm²

absorption band in 9.0-9.1 μm range :

max. absorption in best crystals 0.3 cm⁻¹; worst, 1.5 cm⁻¹

best large crystals, $\sim 1~\text{cm}$, a(3-8 μ m) not more than 0.1 cm⁻¹

 $\alpha(TEA~CO_2~fundamental) = 0.35-0.70~cm^{-1}$

room temperature phase matching ends at 10.2 μm

max. in SHG energy observed for λ = 10.55 μm at T=160-190°C with

 $\Theta_{pm} = 76^{\circ}$; crystals degrade above 400° C

talk about greater than 5 cm crystals;

9.3mm & 9.8mm long with 2 cm² aperture

damage threshold 45 MW/cm²

noted considerable absorption inhomogeneity over face, up to a factor of 3 or 4 obtained an external efficiency of 6-8% (surfaces not AR coated)

maximum energy of SH pulse was 0.16 J

R27 - J.H. Churnside, J.J. Wilson, A.I. Gribenyukov, S.F. Shubin, S.I. Dolgii, Y.M.

Andreev, V.V. Zuev Wave Propagation Lab., Boulder & Institute

for Atmospheric Optics, Tomsk Frequency conversion of a CO₂ Laser with ZnGeP₂

NOAA Technical Memorandum ERL WPL-224 July, 1992

SHG & FHG of CO₂

SHG conversion efficiency 26%

FHG (2 SHG) conversion efficiency 0.04%

R28 - Yu.M. Andreev, S.D. Velikanov, A.S. Yerutin, A.F. Zapol'skii, D.V. Konkin, S.N.

Mishkin, S.V. Smirnov, Yu.N. Frolov, and V.V. Shchurov

All-Russian Scientific-Research Institute of Experimental Physics, Arzamas-16, Nizhnii Novgorod Oblast

Second Harmonic generation from DF laser radiation in ZnGeP₂

Sov. J. Quantum Electronics 22(11) 1035 (November 1992)

Russian ref.: Kvantovaya Elektron.(Moscow) 19 1110 (November 1992)

SHG of DF

pulse length sharp rise with trailing edge: 150 ns(half.max),500 ns (at 0.1)

crystal length 10.1 mm, external efficiency 4%:internal eff. 7.6%

13.6 " " 6.2%; " " 11.8%

R29 - K.L. Vodopyanov General Physics Inst., Moscow Parametric generation of tunable infrared radiation in ZnGeP₂ and GaSe pumped at 3 μm J.Opt.Soc.Am.B **10**(9) 1723-1729 (September 1993)

OPO pumped by Er^{3+} :YAG (2.94µm) or Er^{3+} :Cr³⁺:YSGG(2.79 µm) Type I (o-ee) Type II (o-eo) Property $\theta = 84^{\circ}$, $\omega = 31^{\circ}$ Crystal orientation $\theta = 47^{\circ}, \ \omega = 0^{\circ}$ Range of q variation 76-90 deg 47-49.55 deg Tuning range on um 4-10 5.2-5.6, 6.2-6.7 Crystal length in mm 12 42 Walk-off in mm $0.14(\theta = 48^{\circ})$ $0.11(\theta = 84^{\circ})$ Effective length 12 19 OPG threshold GW/cm² 0.5 0.35 6.5 30 Imax used Max. OPG quantum eff. 3% 17.6% 30 I_{damage} GW/cm² 6.5

R30- A.A. Barykin, S.V. Davydov, V.D. Dorokhov, V.P. Zakharov, & V.V. Butuzov Samarskoe Science-Industrial Union for Automated Systems
 Generation of the second harmonic of CO₂ laser pulses in a ZnGeP₂ crystal Quantum Electronics 23(8) 688-693 (August 1993)
 Russian ref.: Kvantovaya Elektron. 20 794-800 (August 1993)

SHG of CO₂

CRYSTAL: 12.5 X 10.62 x 7.2 mm length

9.3-9.6 μm to 4.6-4.8 μm

R31 - K.L. Vodop'yanov Yu.A. Andreev G.C. Bhar General Physics Inst., Moscow Siberian State Medical University, Tomsk Burdwan Univ., Burdwan, India

Parametric superluminescence in a ZnGeP₂ crystal with temperature tuning and pumping by an erbium laser Quantum Electronics

23(9) 763-766 (Sept. 1993)

Russian ref.: Kvantovaya Elektron. 20 879-882 (September 1993)

OPO

PUMP: Q-switched Er:YSGG laser, $I = 2.79 \mu m$, repition rate 1.2 Hz working energy reached 20 J

single pulse from resonator, 100 ps, energy 0.5-1 mJ

CRYSTAL: length 42 mm in direction of Type II phase matching

 θ = 84° and ϕ = 31°

by temperature tuning could reach 5.3 - 5.9 μm threshold energy density for superluminescence 0.35 GW/cm² working pump energy density 5-10 GW/cm² at superluminescence efficiency of 10% and damage threshold of 35 GW/cm²

R32 - K.L. Vodopyanov

General Physics Inst., Moscow Imperial College, London

2.8 µm Er-laser pumped nonlinear devices

pp.10-13 in **Technical Digest: EQEC'93-EQUAP'93**,Vol.I, Frienze, Italy, 10-13 September 1993, edited by P. de Natale, R. Meucci, S. Pelli

OPO

PUMP: flashlamp pumped Er³⁺:Cr³⁺:YSGG @ λ = 2.8 μ m

Q-switched, single pulses 100 ± 10 ps TEM_{oo} mode, 0.5 mJ after amplification, 2-4 mJ

repetition rate 1-3 sec

when a passive InAs shutter was added, got 30-50 ps pulses

CRYSTAL: length 12 mm for angle tuning

for Type II interaction, length = 42 mm

OPO Type I tuning range 4-10 μm

Type II tuning range 5-6.3 µm, quantum efficiency 18%

Travelling wave OPO threshold 0.35 GW/cm², which is 100 times smaller than the optical damage threshold

R33 - K.L. Vodopyanov

General Physics Inst., Moscow Imperial College, London

2.8 µm Er-laser-pumped non-linear devices

Leituvos fizikos zurnalas 33 (5-6) 301-304 (1993)

OPO

PUMP: mode-locked Sr:Cr:YSGG laser @ λ = 2.8 μ m

single pulses 100 \pm 10 ps, TEM $_{\rm 00}$ mode, about 0.5 mJ

CRYSTALS: L = 11 mm, θ = 47° for Type I phase matching and

L = 42 mm, θ = 84° for Type II phase matching

OPO Type II tuning covered 5-5.3 μm (signal) and 5.9-6.3 μm (idler)

with typical linewidth of 10-20 cm⁻¹

OPG threshold was as low as 0.35 GW/cm²

surface damage threshold for 100 ps 2.8 μm pulses was

30 GW/cm²

Type I had broad OPG lines especially near degeneracy, 1300 cm⁻¹

at $\lambda = 10 \ \mu m$ got linewidth of 50 cm⁻¹

4-10 µm tuning was achieved with 1-2% efficiency

OPG threshold as low as 0.25 GW/cm² for 2.8 μm pump

R34 - Konstantin L. Vodopyanov

General Physics Inst., Moscow Imperial College, London

Wide tuning range OPG's pumped by short Er-laser pulses at λ = 2.8 μm

Advanced Solid State Lasers, OSA Proceedings, Vol. 24, Memphis, TN 30 Jan-2 Feb 1995, 194-197, [1995 Technical Digest, Vol. 8,pp.340-342,WG3-1-3]

PUMP: Er³+:Cr³+:YSGG laser, λ = 2.8 μm, rep rate 3 Hz with active mode locking, τ = 90 ps, with 0.7 mJ with passive mode locking, 30-50 ps pulses, after amplification 3-4 mJ energy per pulse
 Travelling-wave Optical Parametric Generator(TOPG): ZGP tuning range, 3.9-10 μm, for both type I & II OPG pump threshold, 0.25 GW/cm² for 11 mm long crystal Type II had conversion efficiency up to 18% for MW peak power with linewidth 30-40 cm-1
 Type I broader linewidth especially near degeneracy point

R35 - K.L. Vodopyanov V.G. Voevodin Siberian Physical-Technical Inst., Tomsk
 Type I and II ZnGeP2 travelling-wave optical parametric generator tunable between 3.9 and 10 μm
 Optics Communications 117 277-282 (1995)

PUMP: mode locked Er³+:Cr³+:YSGG laser @ λ = 2.8 μ m pulse duration 100 \pm 10 ps, energy 2-3 mJ, rep rate 3 Hz CRYSTAL: Type I (o \rightarrow ee): L= 11 mm, θ = 47° -cut, ϕ = 0° (walk-off 0.13 mm) Type II(o \rightarrow eo): L = 30 & 17 mm, θ = 63.5°, ϕ = 310 (walk-off 0.3 & 0.17 mm)

OPG: Type I tuning range_ 3.9 - 10 μm
Type II tuning ranges_ signal 6 - 10 μm, idler 3.9 - 5.1 μm
OPG linewidths exp. & theor. given at various wavelengths
OPG thresholds for 2.8 μm pump for various lengths given

R36 - Yu.M. Andreev, V.V. Butuzov, G.A. Verozub, A.I. Gribenyukov, S.V. Davydov, and V.P. Zakharov Samara State Research & Production Association of Automatic Systems, Samara, Russia Generation of the second harmonic of pulsed CO_2 -laser radiation in AgGaSe $_2$ and ZnGeP $_2$ single crystals Laser Physics $\mathbf{5}(5)$ 1014-1019 (1995) SHG PUMP CHARACTERISTICS: pulsed electric discharge CO_2 laser output radiation energy 150 mJ output aperture 6.8 mm FWHM of leading spike $\tau_1 \equiv \tau_{0.5} \sim 45$ -50 ns with total pulse duration about 100 ns

maximum gain lines at $\lambda = 9.3, 9.59, 10.26, 10.61 \mu m$

PUMP: Er³+:Cr³+:YSGG laser, $\lambda = 2.8~\mu m$, rep rate 3 Hz with active mode locking, $\tau = 90$ ps, with 0.7 mJ with passive mode locking, 30-50 ps pulses, after amplification 3-4 mJ energy per pulse Travelling-wave Optical Parametric Generator(TOPG): ZGP tuning range, 3.9-10 μm , for both type I & II OPG pump threshold, 0.25 GW/cm² for 11 mm long crystal Type II had conversion efficiency up to 18% for MW peak power with linewidth 30-40 cm-1 Type I broader linewidth especially near degeneracy point

R35 - K.L. Vodopyanov V.G. Voevodin Siberian Physical-Technical Inst., Tomsk
 Type I and II ZnGeP2 travelling-wave optical parametric generator tunable between
 3.9 and 10 μm Optics Communications
 117 277-282 (1995)

PUMP: mode locked Er³+:Cr³+:YSGG laser @ λ = 2.8 μ m pulse duration 100 \pm 10 ps, energy 2-3 mJ, rep rate 3 Hz CRYSTAL: Type I (o \rightarrow ee): L= 11 mm, θ = 47° -cut, ϕ = 0° (walk-off 0.13 mm) Type II(o \rightarrow eo): L = 30 & 17 mm, θ = 63.5°, ϕ = 31° (walk-off 0.3 & 0.17 mm)

OPG: Type I tuning range_ 3.9 - 10 μ m Type II tuning ranges_ signal 6 - 10 μ m, idler 3.9 - 5.1 μ m OPG linewidths exp. & theor. given at various wavelengths OPG thresholds for 2.8 μ m pump for various lengths given

R36 - Yu.M. Andreev, V.V. Butuzov, G.A. Verozub, A.I. Gribenyukov, S.V. Davydov, and V.P. Zakharov Samara State Research & Production Association of Automatic Systems, Samara, Russia Generation of the second harmonic of pulsed CO₂-laser radiation in AgGaSe₂ and ZnGeP₂ single crystals

Laser Physics 5(5) 1014-1019 (1995)
SHG
PUMP CHARACTERISTICS:
pulsed electric discharge CO₂ laser

pulsed electric discharge CO_2 laser output radiation energy 150 mJ output aperture 6.8 mm FWHM of leading spike $\tau_1 \int \tau_{0.5} \sim 45$ -50 ns with total pulse duration about 100 ns maximum gain lines at $\lambda = 9.3, 9.59, 10.26, 10.61 \,\mu\text{m}$

CRY No.	STALS: Thickness	Area of face	Angle of shear	Absorption	on Coefficient
110.	in mm	in mm ²	plane of Xtal	at λ_1	λ_2 in cm ⁻¹
1	12	10 x 15	75 deg	0.7	0.01
2	7.2	12.5 x 10.62	76	0.8	0.4
3	10.4	7.3 x 15	72	0.7	0.01

R37 - Konstantin L. Vodopyanov and Chris C. Phillips

Imperial College, London

Travelling wave mid-IR ZnGeP2 and GaSe optical parametric generators and their spectroscopic applications, pp.170-174 in **Solid State Lasers and Nonlinear Crystals**, 5-7 February 1995, San Jose, CA, edited by Gregory J. Quarles, Leon Esterowitz and L.K. Cheng, SPIE Proceedings Vol. 2379 OPO

PUMP CHARACTERISTICS: Er³+:Cr³+: YSGG laser @ λ = 2.79 µm pulse length τ = 100 ±10 ps, TEM_{oo}, rep rate 3 Hz energy about 0.5 mJ, after passing through amplifier 2-4 mJ

CRYSTAL: absorption at pump wavelength, α < 0.1 cm⁻¹ lengths: Type I, 11 mm; Type II. 42 and 30 m tuning range 4-10 μm for both I & II typical quantum efficiency 1-2 %; for type II, near degeneracy, achieved 18% QPG threshold intensity was 0.24-0.35 GW/cm², a value 100 times smaller than the optical damage threshold

SUMMARY OF RUSSIAN ZnGeP₂ NLO WORK

SUM FREQUENCY GENERATOR (SFG)

Nd:YAG + CO₂

 $CO + CO_2$ 7,14,16,18, 20

 $4.3 + 10.4 \mu m$ 11,14

CO₂ + CO₂ 13,17, 18, 19, 20, 21, 24

SECOND HARMONIC GENERATOR (SHG)

CO₂ 2,6,9,12,13,14,16,17,18,19,20,21,

22,24,26,27,30,36

CO 3,8,17 4.3 μm 11 DF 28

FOURTH HARMONIC GENERATOR (FHG)

CO₂ 3,14,15,18,20,27

OPTICAL PARAMETRIC OSCILLATOR (OPO)

Er:YALO 4,5

Er:Cr:YSGG 11,23,25,29,31,32,33,34,35, 37

Er:YAG 23,25,29

RECENT WESTERN WORK IN ZnGeP2

- C1 P.A. Budni, K. Ezzo, P.G. Schunemann, S. Minnigh, J.C. McCarthy & T.M. Pollak, "2.8 micron pumped optical parametric oscillation in ZnGeP₂", pp.334-338 in **Advanced Solid State Lasers**, Hilton Head, South Carolina, 18-20 March 1991, editors George Dube and Lloyd Chase, Optical Society of America Proceedings, Vol. 10
- PUMP: methane Raman shifted Nd:YAG 1.06 μ m \Rightarrow 2.8 μ m max SRS output 2.1 mi
- CRYSTAL: 6x6x18 mm, faces cut normal to <102> direction $\alpha(2.8\mu\text{m}) = 0.06 \text{ cm}^{-1}$, $\alpha(5.6\mu\text{m}) < 0.02 \text{ cm}^{-1}$
- OPO RESULTS: Type I phase matching. For Input, 2.1 mj, spot size 1.2 mm, 8-12 ns pulsewidth get peak power density up to 45 MW/cm², 150 μj per pulse, for an optical efficiency of 7% Threshold for OPO output, 18-20 MW/cm²
- C2 Norman P. Barnes, "Tunable mid-infrared sources using second-order nonlinearities", International Journal of Nonlinear Optical Physics, 1, 639-672 (1991)

internal phase-matching angles vs wavelength for 1.73 & 2.10 μ m pumps, range of incident angles 63° for 1.73 μ m; 13° for 2.10 μ m

- C3 P.A. Budni. P.G. Schunemann, M.G. Knights, T.M. Pollak & E.P. Chicklis, "Efficient, high average power optical parametric oscillator using ZnGeP₂", pp. 380-383 in **Advanced Solid State Lasers,** Sante Fe, New Mexico, 17-19 February **1992**, editors Lloyd L. Chase & Albert A. Pinto, OSA Proceedings, Vol. 13
- PUMP: 2μm from diode pumped, repetitively Q-switched Tm,Ho:YLF oscillator amplified by tungsten-lamp pumped Er,Tm,Ho:YLF amplifier. At 77K, 40 W average power output, pulse repetition frequency (PRF) 1-90 kHz, FWHM pulsewidth 15-525 ns. A 2-pass pre-amplifier output is 10 W: with 2 single pass stages added, the total power output > 40 W
- CRYSTAL: 6x6x12 mm, boule grown along [112], α (2.05 μ m)=0.26 cm⁻¹ Type I phase matching, θ = 55°.
- OPO RESULTS: Using 10 W input: rep rate 2.5 kHz, 23 ns pulsewidth, 28.5% slope efficiency; 4 kHz, 27 ns, 27.3%, highest overall efficiency, 18%; using 13 W input: 10 kHz, 28 ns, highest total power, 1.6 W Continuous tunability from 3.45 5.05 μm.

- C4 M. Knights & P. Budni, Tunable Mid-IR Laser Program, Final Technical Report, WL-TR-92-5031, August 1992, Wright Laboratory, Solid State Electronics Directorate, WL/ELOS, Contract F33615-89-C-1059
 OPO
- PUMP: 2 μ m holmium YLF laser and amplifier, TEM $_{00}$ output average power of 44 Watts with pulsewidths of 25 ns @ 10 kHz Pump repetition rates of 2.5, 4, 10, 20 and 30 kHz had pump pulsewidths of 23, 27, 28, 60 and 97 nsecs respectively
- CRYSTAL: type I phase matching, $\theta=55^{\circ}$, $6\times6\times12$ mm experimentally verified 2 μ m pumped phase matching curve over 3.45-5.05 μ m range energy slope conversion efficiency of 28.5% and overall conversion to 18% achieved @ 2.5 kHz; conversion efficiency of 27.3% @ 4 kHz demonstrated high PRF operation: 2-30 kHz demonstrated 1.6 W average power @ 10 kHz for 13 W input: 1.4 W @ 20 kHz; 0.8 W @ 30 kHz
- C5 M. Knights & P. Budni, Characterization of AgGaSe₂ and ZnGeP₂ OPO's Pumped with High Power 2 Micron Lasers, Final Technical Report, WL-TR-93-5016, November 1992, Wright Laboratory, Solid State Electronics Directorate, WL/ELOS, Contract F33615-89-C-1059, modification P0007 OPO
- PUMP: Cryogenically cooled, diode pumped Ho:YLF @ 2µm 3W CW or Q-switched @ 1.5 kHz with 18-nsec FWHM high power thermal effects used 20 W CW multimode tungsten pumped LN₂ oscillator
- OPO RESULTS: absorption coefficient α_{o} is temperature dependent.

 $\alpha_0(300^{\circ}\text{K}) = 2 \times \alpha_0(77^{\circ}\text{K})$

 α_e shows no change with temperature beam diameter 0.57 mm $1/e^2$ points

- For high loss ZGP crystals (α_o = 0.36cm⁻¹),length 14.5 mm long slope effociency is 6% @300°K and 27% @ 77°K with α_o = 0.26 cm⁻¹ crystal, slope efficiency is 37.5%
- C6 P.G. Schunemann, P.A. Budni, M.G. Knights, T.M. Pollak, E.P. Chicklis, & C.L. Marquardt, "Recent advances in ZnGeP₂ mid-IR optical parametric oscillators", 131-133, **Advanced Solid-State Lasers / Compact Blue-Green Lasers**, New Orleans, Louisiana, 1-4 February 1993, Optical Society of America 1993 Technical Digest Series Vol.2; pp. 166-168 in **OSA Proceedings on Advanced Solid-State Lasers, Vol 15**, A.A. Pinto and T.Y. Fan, ed., (Optical Society of America, Washington, DC 1993)

OPO

PUMP LASER: diode pumped A/O Q-switched Tm:Ho:YLF @ 77 K λ = 2.05 μ m, TEM_{oo} mode, linearly polarized, pulse width 18 \pm 1 nsec (FWHM) rep rate 1500 Hz, 1/e² diameter = 0.57 mm at center of Xtal

CRYSTALS: 6x6x11 mm³ & 4.5X4.5x14.6 mm³

Orientation $\Theta = 55^{\circ}$ for Type I phasematch @ 2.05 μ m pump

Absorption coefficients @ 2.05 μ m : (α_0 =0.26; α_e =0.58) cm⁻¹ &

 $(\alpha_0=0.38; \alpha_e=0.77)$ cm⁻¹ respectively @ RT

In situ: high loss crystal @ 2.05 µm measured

 $\alpha_0 = 0.36 \pm 0.01 \text{ cm}^{-1}$; $\alpha_e = 0.78 \pm 0.01 \text{ cm}^{-1}$ @ RT;

 $\alpha_0 = 0.17 \pm 0.01 \text{ cm}^{-1}$; $\alpha_e = 0.77 \pm 0.01 \text{ cm}^{-1}$ @ LNT

AR Coatings: each 2.05 μm & 3.5-5.0 μm

Laser damage the shold: > 1.2 J/cm²

OPO RESULTS: Collinearly pumped & doubly resonant

Low loss Xtal @ RT: total power conversion efficiency = 26%

with 679 mW threshold, 37% slope

maximum sustained power output: 585 mW @ pump

fluence ≈ 1.2 J/.cm²

High loss Xtal: @ RT, threshold was 520 mW and slope ≈ 6% @LNT, threshold ≈ 400 mW and slope efficiency ≈ 25% after realignment at LNT, threshold was 295 mW and slope efficiency was 27%. Pumping with 2.3 W obtained OPO output of 552 mW, an absolute power conversion efficiency of 24%

C7 - M.G. Knights, P.A. Budni, P.G. Schunemann, T.M. Pollak, & E.P. Chicklis, "Multi-watt mid-IR optical parametric oscillator using ZnGeP2", 259-261, OSA Topical Meeting on Advanced Solid State Lasers, Salt Lake City, UT, 7-10 Feb 1994, OSA 1994 Technical Digest Vol.20 OPO

PUMP LASER: Q-switched Tm,Ho:YLF @2.06μm + single-pass rod amplifier capable of 9 W, 6.5 W incident on OPO corresponding to 1.6 mJ/pulse @ 4 KHz. Focussed to beam waist of 600 µm, this yielded 1.15 J/cm² or 144 MW/cm² in 8 nsec.

CRYSTAL: 6x6x11 mm, $\Theta = 55^{\circ}$, $\alpha_0(2.05\mu\text{m}) = 0.26 \text{ cm}^{-1}$

OPO RESULTS: Doubly resonant oscillator with double degenercy point at 4.1 um.

Highest average power achieved was 2.66 W with conversion efficiency of 40%. [3.3 W output shown at meeting]. Highest conversion efficiency was 46% @ 4.65 W drive level. First 4 data points yield a slope efficiency of ≈ 65% which extrapolates to a threshold of 1.32 W pump input.

C8 - C.L. Marguardt, W.T. Whitney, B.J. Feldman, G.C. Catella, D.S. Burlage, M.G. Knights, P.A. Budni, & P.G. Schunemann, "Thermal effects in zinc germanium phosphide optical parametric oscillators", 201, CLEO'94, Summaries of papers presented ay the Conference on Lasers and Electro-Optics, Anaheim, CA, 8-13 May 1994, Optical Society of America 1994 Technical Digest Series Vol. 8

C9 - P.D. Mason, D.J. Jackson & E.K. Gorton CO₂ laser frequency doubling in ZnGeP₂ Optics Comm. 110 163-166 (1994) Erratum Optics Comm. 114 529 (1995)

SHG

PUMP: TEA CO₂ laser. single axial mode, 9P(20) transition, λ = 9.55 μ m. Typical peak power 14 kW, pulse duration 240 ns (FWHM)

CRYSTAL: 7.7x7.5 mm aperture, 1 cm long, cut 70° to c-axis

 $\alpha(9.6 \ \mu\text{m}) = 0.56 \ \text{cm}^{-1}, \ \alpha(4.8 \ \mu\text{m}) = 0.155 \ \text{cm}^{-1}$

RESULTS: For 9.55 μm, phase match angle 67.7°

Maximum peak conversion efficiency was 8.1% for a pump internal intensity of 30 MW/cm² and energy density 18 J/cm²

C10 - Norman P. Barnes, Keith E. Murray, Mehendra G. Jani, & Thomas M. Pollak, WG5-1-3, 346-349, "ZnGeP₂ parametric amplifier", **Technical Digest- Advanced Solid State Lasers**, Memphis TN, 30 Jan- 2 Feb 1995, Optical Society of America OPA

PUMP: Ho:Tm:Er:YLF @ 2.06 μm, pulse length ≈50 ns, 30 mJ

CRYSTAL: 9 mm long

SIGNAL: 3.39 µm from HeNe was absorbed in ZGP yielding gain of ≈0.7 single pass, small signal gain was 10 for 2.064 µm

C11 - J.M Auerhammer, A.F.G. van der Meer, & P. W. van Amersfoort, "Effecient frequency doubling of picosecond pulses of a free-electron laser in ZnGeP₂", Paper CTuI20, CLEO/QELS 95, Baltimore, MD, 23 May 1995, CLEO'95, Vol. 15,1995 Technical Digest Series OSA, P.99, (p.87 Advance Program) SHG

PUMP: free-electron laser, FELIX, λ = 5.5-9.0 μ m, high-power, short-pulse external efficiencies 49% - 15%

At $\lambda = 7.8 \ \mu m$, generated 14 mW of SHG average power, 0.8 MW peak power, pulse energy 0.8 μ J.

CRYSTAL: 7 mm long, Type I phase matching

C12 - J.M. Auerhammer, A.F.G. van-der-Meer, P.W. van-Amersfoort, Q.H.F. Vrehen & E.R. Eliel, "Effecient frequency doubling of ps-pulses from a free-electron laser in ZnGeP₂", Optics Communications, **118** 85-89 (1995)

PUMP: FELIX (free electron laser for infrared experiments), p-polarized, 5-110 μ m, 1 ps pulses at 1 GHz rep rate contained inside 'macropulse' typically 5 μ s repeated every 200 ms. Average power of laser 10-100 mW. Experiments done at λ = 5.5, 6.3, 7.8, 8.3 & 9.0 μ m. Measured external conversion efficiences η_{ext} are respectively: 0.48, 0.46. 0.36, 0.29 & 0.12, for 1 MW incident power.

CRYSTAL: 7 mm long, Type I phase matching

APPENDIX

The following pages are a bibliography of nonlinear optics use of ZnGeP2, listed alphabetically by first author.

Andreev, Y. M., V. G. Voevodin, A. I. Gribenyukov, O. Y. Zyryanov, I. I. Ippolitov, A. N. Morozov, A. V. Sosnin and G. S. Khmel'nitskii. (1984). "Efficient generation of the second harmonic of tunable CO2 laser radiation in ZnGeP2." Soviet Journal of Quantum Electronics. 14 1021-1022 Russian reference: Kvantovaya Elektron. (Moscow) 11,1511-1512 (August 1984).

Andreev, Y. M., T. V. Vedernikova, A. A. Betin, V. G. Voevodin, A. I. Gribenyukov, O. Y. Zyryanov, I. I. Ippolitov, V. I. Masychev, O. V. Mitropol'skii, V. P. Novikov, M. A. Novikov and A. V. Sosnin. (1985). "Conversion of CO2 and CO laser radiations in a ZnGeP2 crystal to the 2.3-3.1 μ spectral range." Soviet Journal of Quantum Electronics. 15 1014-1015 Russian ref.: Kvantovaya Elektron. 12 1535-1537 (July 1985).

Andreev, Y. M., V. G. Voevodin, A. Gribenyukov, O. I. Zyrianov, I. I. Ippolitov, A. N. Morozov, A. V. Sosnin and G. S. Khmel'nitskii."ZnGeP2 second-harmonic generator for a CO2 laser" 113-119. Spectroscopic Methods of Atmospheric Sounding (Monitoring the Atmosphere). I. V. Samokhvalov. Novosibirsk, Siberia.Izdatel'stvo Nauk (Nauka, Sib. Otd., Novosibirsk, USSR). (1985).Spektrosk. Metody Zondirovaniya Atmos.

Andreev, Y. M., V. Y. Baranov, V. G. Voevodin, P. P. Geiko, A. I. Gribenyukov, S. V. Izyumov, S. M. Kozochkin, V. D. Pis'mennyi, Y. A. Satov and A. P. Strel'tsov. (1987). "Efficient generation of the second harmonic of a nanosecond CO2 laser radiation pulse." Soviet Journal of Quantum Electronics. 17 1435-6 Russian Ref.: Kvantovaya Elektronika 14 2252-2254 (Nov. 1987).

Andreev, Y. M., V. G. Voevodin, A. I. Gribenyukov and V. P. Novikov. (1987). "Mixing of frequencies of CO₂ and CO lasers in ZnGeP₂." Sov.J.Quantum Electron. **17** 748-749 Russian ref: Kvantovaia Elektronika **14** 1177-1178 (June,1987).

Andreev, Y. M., V. G. Voevodin, P. P. Geiko, A. I. Gribenyukov, V. V. Zuev, A. S. Solodukhin, S. A. Trushin, V. V. Churakov and S. F. Shubin. (1987). "Transformation of the frequencies of nontraditional(4.3 and 10.4μ) CO2 laser radiation bands in ZnGeP2." Soviet Journal of Quantum Electronics. 17 1362-3 Russian Russian ref: Kvantovaia Elektronika 14 2137-2138 (Nov. 1987).

Andreev, Y. M., A. D. Belykh, V. G. Voevodin, P.P.Geiko, A. I. Gribenyukov, V. A. Gurashvili and S. V. Izyumov. (1987). "Doubling of the emission frequency of CO lasers with an efficiency of 3%." Sov. J. Quantum Electron. 17 490-491 Russian ref.: Kvantovaya Elektron. 14 782-783 (April 1987).

Andreev, Y., A. I. Gribenyukov, V. V. Zuev, N. V. Karlov, V. D. Karyshev, A. V. Kisletsov, I. O. Kovalev, A. V. Korablev, G. P. Kuz'min, L. A. Kulevskii and A. A. Nesterenko. (1987). "Second-harmonic generation in ZnGeP2 pumped by a continuously tunable CO2 laser." Sov.Tech.Phys.Lett. 13 595-596 Russian ref.: Pis'ma v Zhurnal Tekhnicheskoi Fiziki 13 1423-1426 (12 Dec 1987).

Andreev, Y. M., V. G. Voevodin, P. P. Geiko, A. I. Gribenyukov, V. V. Zuev and V. E. Zuev. "Effective source of coherent radiation based on CO₂ lasers and ZnGeP₂ frequency converters" 300-303. Laser and Optical Remote Sensing: Instrumention & Techniques. O. S. o. America. North Falmouth, MA; 28 Sept.- 1 Oct. 1987.OSA. (1987).18.

Andreev, Y. M., P. P. Geiko, V. V. Zuev, V. E. Zuev, O. A. Romanovskii and S. F. Shubin. "Advances in gas-analyzers based on IR molecular lasers" 152-155. Laser & Optical Remote Sensing: Instrumentation & Techniques. North Falmouth, MA, 28 Sept-1 Oct 1987. Technical Digest series. (1987).18.

Andreev, Y. M., P. P. Geiko and V. V. Zuev."High-efficiency frequency conversion of IR lasers with ZnGeP2 and CdGeAs2" 190-192. Advances in Laser Science III. Third International Laser Science Conference. A. C. Tam, J. L. Gole and W. C. Stwalley. Atlantic City, NJ USA 1-4 Nov 1987.AIP Conference Proceedings. (1988).AIP Conference Proceedings. 172A.

Andreev, Y. M., P. P. Geiko, V. V. Zuev, O. A. Romanovskii and S. F. Shubin. "Control of gas pollution of air medium with the aid of CO₂ and CO lasers equipped with frequency converters" 221-222. XIII International Conference on Coherent & Nonlinear Optics. Minsk, Russia 6-9 September 1988. (1988). Part II, Sections IX-XVI.

Andreev, Y. M., P. P. Geiko, V. V. Zuev and O. A. Romanovskii. "Gas analysis using CO₂ laser frequency converters" 193-5. Advances in Laser Science III. Third International Laser Science Conference. ed., A.

C. Tam, J. L. Gole and W. C. Stwalley. Atlantic City, NJ USA 1-4 Nov 1987. American Institute of Physics Conference Proceedings. (1988). AIP Conference Proceedings. 172.

Andreev, Y. M., V. G. Voevodin, A. I. Gribenyukov, V. N. Davydov, V. I. Zhuravlev, V. A. Kapitanov, T. D. Lezina, G. A. Struchebrov and G. S. Khmel'nitskii. (1988). "Beam-path gas analyzer based on a tunable CO₂ laser." J. Applied Spectroscopy. 47 662-666 Russian ref.: Zhurnal Prikladnoi Spektroskopii 47(1) 15-20 (July, 1987).

Andreev, Y. M., A. N. Bykanov, A. I. Gribenyukov, V. V. Zuev, V. D. Karyshev, A. V. Kisletsov, I. O. Konov, G. P. Kuz'min, A. A. Nesterenko, A. E. Osorgin, Y. M. Starodumov and N. I. Chapliev. (1990). "Conversion of pulsed laser radiation from the 9.3-9.6 μm range to the second harmonic in ZnGeP2 crystals." Soviet Journal of Quantum Electronics. 20 410-414 Russian Ref.: Kvantovaya Elektron. 17 476-480 (April 1990).

Andreev, Y. M., P. P. Geiko, G. M. Krekov and O. A. Romanovskii."Detection of trace concentration of some simple pollutants in Tomsk" 367-370. Tenth All-Union Symposium and School on High-Resolution Molecular Spectroscopy. L. N. Sinitsa. Omsk, Russia, 2-9 June 1991.SPIE. (1991).SPIE Proceedings Series.1811.

Andreev, Y. M., S. D. Velikanov, A. S. Yerutin, A. F. Zapol'skii, D. V. Konkin, S. N. Mishkin, S. V. Smirnov, Y. N. Frolov and V. V. Shchurov. (1992). "Second Harmonic generation from DF laser radiation in ZnGeP₂." Sov. J. Quantum Electron. **22** 1035 Russian ref.: Kvantovaya Elektron.(Moscow) **19** 1110 (November 1992).

Andreev, Y. M., V. V. Butuzov, G. A. Verozub, A. I. Gribenyukov, S. V. Davydov and V. P. Zakharov. (1995). "Generation of the second harmonic of pulsed CO₂-laser radiation in AgGaSe₂ and ZnGeP₂ single crystals." Laser Physics. **5** (5) 1014-1019

Andreeva, N. P., S. A. Andreev, I. N. Matveev, S. M. Pshenichnikov and N. D. Ustinov. (1979). "Parametric conversion of infrared radiation in zinc-germanium diphosphide." Soviet Journal of Quantum Electronics. 9 208-210 Russian reference: Kvantovaya Elektron. (Moscow) 6 357-359 (1979).

Andreeva, L. I., K. L. Vodop'yanov, S. A. Kaidalov, Y. M. Kalinin, M. E. Karasev, L. A. Kulevskii and A. V. Lukshev. (1986). "Picosecond erbium-doped YAG laser (λ =2.94 μ) with active mode locking." Sov.J. Quantum Electron. **16** 326-333 Russian Ref.: Kvantovaya Elektron. **13** 499-509 (March 1986).

Auerhammer, J. M., A. F. G. van-der-Meer and P. W. van-Amersfoort. "Efficient frequency doubling of picosecond pulses of a free-electron laser in ZnGeP₂" 99. CLEO'95, Summaries of Papers. O. S. o. America. Baltimore, MD, 22-26 May 1995.OSA. (1995).15, 1995 Technical Digest Series.

Auerhammer, J. M., A. F. G. van-der-Meer, P. W. van-Amersfoort, Q. H. F. Vrehen and E. R. Eliel. (1995). "Efficient frequency doubling of ps-pulses from a free-electron laser in ZnGeP₂." Optics Comm. **118** 85-89

Barnes, N. P. (1991). "Tunable mid-infrared sources using second-order nonlinearities." International Journal of Nonlinear Optical Physics. 1 639-672

Barnes, N. P., K. E. Murray, M. G. Jani and T. M. Pollak."ZnGeP₂ parametric amplifier" WG5-1-3, 346-349. **Technical Digest- Advanced Solid State Lasers.** O. S. o. America. Memphis TN 30 Jan- 2 Feb 1995.OSA. (1995).

Barykin, A. A., S. V. Davydov, V. D. Dorokhov and V. V. Butuzov. (1993). "Generation of the second harmonic of CO₂ laser pulses in a ZnGeP₂ crystal." Quantum Electronics. **23** 688-693 Russian ref.: Kvantovaya Elektron. **20** 794-800 (August 1993).

Beregulin, E. V., P. M. Valov, T. V. Rybakova and I. D. Yaroshetskii. (1974). "Possibility of using gallium selenide crystals for conversion of infrared light into near infrared and visible radiation." Sov. Phys. Semiconductors. 8 122-123 Russian ref.: Fiz. Tekh. Poluprovodn. 8(1) 189-192 (January 1974).

Betin, A. A., V. G. Voevodin, K. V. Ergakov, A. V. Kirsanov and V. P. Novikov. (1991). "Generator of infrared radiation at the second-harmonic frequency of a TEA CO₂ laser." Sov.J. Quantum Electron. **21** 735-738 Russian Ref.:

- Kvantovaya Elektron. 18 812-816 (July 1991).
- Bhar, G. C. and G. C. Ghosh. "Evaluation of ZnGeP2 crystal for temperature dependent phase-matched nonlinear interactions". 129-132. <u>Proceedings of the 4th International Conference on Ternary and Multinary Compounds.</u> <u>Tokyo.1980.19</u>, Supplement 19-3. Japanese Journal of Applied Physics.(1980).
- Bhar, G. C., L. K. Samanta, D. K. Ghosh and S. Das. (1987). "Tunable parametric ZnGeP2 crystal oscillator." Soviet Journal of Quantum Electronics. 17 860-861 Russian reference: Kvantovaya Elektron.(Moscow) 14 1361-1363 (July 1987).
- Bhar, G. C. and N. P. Ghosh. (1988). "Broadband tuning in an infrared parametric oscillator." Physica Status Solidi. a 106 K93-K96
- Bhar, G. C., S. Das, U. Chatterjee and K. L. Vodopyanov. (1989). "Temperature-tunable second-harmonic generation in zinc germanium diphosphide." Applied Physics Letters. **54** 313-314
- Bhar, G. C., S. Das, V. V. Rampal and R. K. Tyagi. (1990). "Temperature effects in ZnGeP2 nonlinear devices." Journal of Physics D: Applied Physics. 23 121-122
- Bhar, G. C. and U. Chatterjee. (1992). "Nonlinear devices based on some crystals of current interest." Indian Journal of Physics, Part B. 66B 107-121
- Bhar, G. C. "Silver thiogallate and related diamond-like semiconductors for nonlinear optical laser devices" 653-659. Proceedings of the 9th International Conference on Ternary and Multinary Compounds ICTMC-9. K. Masumoto, T. Irie, S. Iida and N. Yamamoto. Yokohama, Japan, 8-12 August 1993. Japanese J. Appl. Phys. (1993).32 Suppl. 32-3.
- Bhar, G. C., P. K. Datta and S. Das."In search of noncritically phase-matched nonlinear devices with chalcopyrite crystals" 120-122. Proceedings of the 9th International Conference on Ternary and Multinary Compounds ICTMC-9. K. Masumoto, T. Irie, S. Iida and N. Yamamoto. Yokohama, Japan, 8-12 August 1993. Japanese J. Applied Physics. (1993).32 Supplement 32-3.

- Boyd, G. D., W. B. Gandrud and E. Buehler. (1971). "Phase-Matched Up Conversion of 10.6μ Radiation in ZnGeP2." Applied Physics Letters. 18 446-448
- Boyd, G. D., E. Buehler and F. G. Storz. (1971). "Linear and nonlinear optical properties of ZnGeP2 and CdSe." Applied Physics Letters. 18 301-304
- Boyd, G. D., E. Buehler, F. G. Storz and J. H. Wernick. (1972). "Linear and Nonlinear Optical Properties of Ternary AllBIVCV2 Chalcopyrite Semiconductors." IEEE Journal of Quantum Electronics. **QE-8** 419-426
- Boyd, G. D., T. J. Bridges, C. K. N. Patel and E. Buehler. (1972). "Phase-matched submillimeter wave generation by difference-frequency mixing in ZnGeP2." Applied Physics Letters. 21 553-555
- Boyd, G. D., H. M. Kasper, J. H. McFee and F. G. Storz. (1972). "Linear and nonlinear optical properties of some ternary selenides." IEEE Journal of Quantum Electronics. **QE-8** 900-908
- Budni, P. A., K. Ezzo, P. G. Schunemann, S. Minnigh, J. C. McCarthy and T. M. Pollak."2.8 micron pumped optical parametric oscillation in ZnGeP₂" 335-338. **Advanced Solid-State Lasers.** G. Dube and L. Chase. Hilton Head, South Carolina, 18-20 March 1991.Optical Society of America. (1991).OSA Proceedings.10.
- Budni, P. A., P. G. Schunemann, M. G. Knights, T. M. Pollak and E. P. Chicklis. "Efficient, high average power optical parametric oscillator using ZnGeP₂" 380-383. **Advanced Solid-State Lasers.** L. L. Chase and A. A. Pinto. Sante Fe, New Mexico, 17-19 February 1992. Optical Society of America. (1992). OSA Proceedings. 13.
- Catella, G. C., J. H. Bohn, D. A. Roberts and J. William R. Cook. "Application analysis of new nonlinear materials". <u>Growth. Characterization. and Applications of Laser Host and Nonlinear Crystals</u>. **1104**. J. T. Lin. SPIE.Bellingham, WA. (1989).
- Catella, G. C., D. S. Burlage, J. D. Beasley and C. L. Marquardt."Modeling and comparison with recent lensing experiments in AgGaSe₂ and ZnGeP₂"

272-280. Nonlinear Optics for High Speed Electronics and Frequency Conversion. N. Peygambarian, H. Everitt, R. C. Eckardt and D. D. Lowenthal. Los Angeles, CA, 24-26 January 1994.SPIE. (1994).2145.

Churnside, J. H., J. J. Wilson, A. I. Gribenyukov, S. F. Shubin, S. I. Dolgii, Y. M. Andreev and V. V. Zuev. "Frequency conversion of a CO₂ Laser with ZeGeP₂" July 1992. Wave Propagation Laboratory, National Oceanic and Atmospheric Administration (NOAA), Boulder, Colorado. (1992).

CookJr., W. R. and R. A. Iannini. "Selection and Growth of New Opto-Electronic Crystals" September 1988. Materials Laboratory, Wright-Patterson Air Force Base, Ohio. (1988).

Dmitriev, V. G., G. G. Gurzadyan and D. N. Nikogosyan. (1991). Handbook of Nonlinear Optical Crystals.A. E. Siegman.Springer Series in Optical Sciences.64. Springer-Verlag.Berlin.

Gandrud, W. B., G. D. Boyd and E. Buehler. (1971). "Phase-Matched Upconversion of 10.6-μ Radiation in ZeGeP2." IEEE J. Quantum Electron. QE-7 307-308

Goodman, C. H. L. (1991). "Semiconductor and non-linear optical materials." Semicond. Sci. Technol. 6 725-729

Guenter, P. (1980). "Electro-optical and nonlinear-optical materials." Ferroelectrics. 24 35-42

Knights, M. and P. Budni. "Tunable Mid-IR Laser Program, Final Technical Report" WL-TR-92-5031, August 1992. Wright Laboratory, Solid State Electronics Directorate, WL/ELOS. (1992).

Knights, M. G. and P. A. Budni. "Characterization of AgGaSe₂ and ZnGeP₂ OPO's Pumped with High Power 2 Micron Lasers" WL-TR-93-5016, November 1992. Wright Laboratory, Solid State Electronics Directorate, WL/ELOS. (1993).

Knights, M. G., P. A. Budni, P. G. Schunemann, T. M. Pollak and E. P. Chicklis."Multi-watt mid-IR optical parametric oscillator using ZnGeP₂" 259-261. OSA Topical Meeting on Advanced Solid State Lasers, Technical Digest. Salt Lake City, UT, 7-10 Feb 1994.OSA. (1994).OSA

Proceedings.20.

Marquardt, C. L., W. T. Whitney, B. J. Feldman, G. C. Catella, D. S. Burlage, M. G. Knights, P. A. Budni and P. G. Schunemann. "Thermal effects in zinc germanium phosphide optical parametric oscillators" 201. CLEO'94, Summaries of papers presented ay the Conference on Lasers and Electro-Optics. O. S. o. America. Anaheim, CA, 8-13 May 1994.OSA. (1994).1994 Technical Digest Series.8.

Marshall, L. R. "Efficient multiwatt 2-5 μm tunable sources" Advance Program p. 128. CLEO/QELS '96. Anaheim, CA, 2-7 June 1996.OSA. (1996).

Mason, P. D., D. J. Jackson and E. K. Gorton. (1994). "CO₂ laser frequency doubling in ZnGeP₂." Optics Comm. **110** 163-166 Errattum: Optics Comm. **114** 529 (1995).

Nichols, E. R., J. John C. Corbin and V. L. Donlan."A Review of Parametric Oscillators and Mixers and an Evaluation of Materials for 2-6µm Applications" July 1974. Air Force Avionics Laboratory. (1974).

Nikogosyan, D. N. (1977). "Nonlinear optics crystals (review and summary of data)." Sov. J. Quantum Electron. 7 1-13 Russian ref: Kvantovaya Elektron. 4 5-26 (1977).

Scholl, F. W. and C. L. Tang. (1973). "Nonlinear optical properties of II-IV-V2 semiconductors." Physical Review B. **B8** 4607-4611

Schunemann, P. G. and T. M. Pollak."Progress in the development of ZnGeP₂ for optical parametric oscillator applications" 332-334. **Advanced Solid-State Lasers.** G. Dube and L. Chase. Hilton Head, South Carolina 18-20 March 1991.Optical Society of America. (1991).OSA Proceedings.10.

Schunemann, P. G., P. A. Budni, M. G. Knights, T. M. Pollak, E. P. Chicklis and C. L. Marquardt. "Recent advances in ZnGeP₂ mid-IR optical parametric oscillators" 131-133. **Technical Digest, Advanced Solid-State**Lasers / Compact Blue-Green Lasers. New Orleans, Louisiana, 1-4
February 1993. Optical Society of America. (1993).1993 Technical Digest

Series.2.

Shay, J. L. and J. H. Wernick. (1975). Ternary Chalcopyrite Semiconductors: Growth, Electronic Properties and Applications. Pergamon Press. New York.

Tang, C. L. and L. K. Cheng. (1995). Fundamentals of Optical Parametric Processes and Oscillators.130. V. S. Letokhov, C. V. Shank, Y. R. Shen and H. Walther.Laser Science and Technology.20. Harwood Academic Publishers.Amsterdam.

Tucker, J. E., C. L. Marquardt, S. R. Bowman and B. J. Feldman. "Transient thermal lensing in ZnGeP₂ OPO material" 245-246. **CLEO' 95, Summaries of Papers.** O. S. o. America. Baltimore, MD, 22-26 May 1995.OSA. (1995).15, 1995 Technical Digest Series.

Tucker, J. E., C. L. Marquardt, S. R. Bowman and B. J. Feldman. (1995). "Transient thermal lens in ZnGeP₂ crystal." Applied Optics. **34** (15) 2678-2682

Vodop'yanov, K. L., V. G. Voevod, A. I. Gribenyukov and L. A. Kulevskii. (1985). "Picosecond parametric superluminescence in the ZnGeP2 crystal." Bulletin of the Academy of Sciences of the USSR, Physical Series. 49 146-149 Russian ref.: Izvestiya Akademii Nauk SSSR, Seriya Fizicheskaya 49 (3) 569-572 (1985).

Vodop'yanov, K. L., V. G. Voevodin, A. I. Gribenyukov and L. A. Kulevskii. (1987). "High-efficiency picosecond parametric superradiance emitted by a ZnGeP2 crystal in the 5-6.3 micron range." Sov.J.Quantum Electron. 17 1159-1161 Russian ref: Kvantovaia Elektronika 14 1815-1819 (Sept. 1987).

Vodop'yanov, K. L., Y. A. Andreev and G. C. Bhar. (1993). "Parametric superluminescence in a ZnGeP₂ crystal with temperature tuning and pumping by an erbium laser." Quantum Electronics. **23** 763-765 Russian ref.: Kvantovaya Elektron. **20** 879-882 (September 1993).

Vodopyanov, K. L., L. A. Kulevskii, V. G. Voevodin, A. I. Gribenyukov, K. R. Allakhverdiev and T. A. Kerimov. (1991). "High efficiency middle IR

parametric superradiance in ZnGeP₂ and GaSe crystals pumped by an erbium laser." Optics Communications. 83 322-326

Vodopyanov, K. L., L. A. Kulevskii, A. I. Gribenyukov and K. R. Allakhverdiev. (1991). "High efficiency middle IR parametric superradiance in ZnGeP2 and GaSe crystals pumped by an erbium laser." Journal de Physique IV: Colloque C7, supplement au Journal de Physique III. 1 C7-391 - C7-394

Vodopyanov, K. L."2.8 μm Er-laser pumped nonlinear devices" 10-13. **Technical Digest: EQEC'93-EQUAP'93,Vol.I.** P. d. Natale, R. Meucci and S. Pelli. Frienze, Italy, 10-13 September 1993. European Physical Society. (1993).1.

Vodopyanov, K. L. (1993). "Parametric generation of tunable infrared radiation in $ZnGeP_2$ and GaSe pumped at 3 μ m." J. Opt. Soc. Am. B. **B10** 1723-1729

Vodopyanov, K. L. (1993). "2.8 μm Er-laser-pumped non-linear devices." Leituvos fizikos zurnalas. **33** (5-6) 301-304

Vodopyanov, K. L."Wide tuning range OPG's pumped by short Er-laser pulses at $\lambda = 2.8 \ \mu m$ " WG3-1-3, 340-342. **Technical Digest- Advanced Solid State Lasers.** O. S. o. America. Memphis TN 30 Jan - 2 Feb 1995.OSA. (1995).1995 Technical Digest Series.

Vodopyanov, K. L. and C. C. Phillips."Travelling wave mid-IR ZnGeP2 and GaSe optical parametric generators and their spectroscopic applications" 170-174. Solid State Lasers and Nonlinear Crystals. G. J. Quarles, L. Esterwitz and L. K. Cheng. San Jose, CA, 5-7 Feb 1995.SPIE. (1995).2379.

Vodopyanov, K. L. and V. G. Voevodin. (1995). "Type I and II ZnGeP₂ travelling-wave optical parametric generator tunable between 3.9 and 10 μm." Optics Comm. **117** 277-282

Zuev, V. E., Y. M. Andreev, V. G. Voevodin, A. I. Gribenyukov, V. A. Kapitanov, A. V. Sosnin, G. A. Stuchebrov and G. S. Khmelnitskii. "Mutlifrequency dual sensing of the atmospheric gaseous constituents using the first and second harmonics of a tunable CO₂ laser radiation" 108-110. **Proc.**Thirteenth International Laser Radar Conference. Toronto,

Canada.(1986).NASA Conf. Publ. No. 2413.

Zuev, V. E."Development of lasers and spectral equipment for measurement of atmospheric molecular gases" 18-21. Laser and Optical Remote Sensing: Instrumentation and Techniques. O. S. o. America. North Falmouth, Mass., 28 Sept.-1 Oct 1987.OSA. (1987).1987 Technical Digest Series.18.

Zuev, V. E. "Spectroscopic studies of laser sounding of the atmosphere" 119-121. International Laser Radar Conference. Innichen-San Candido, Italy 20-24 June 1988.(1988).

Zuev, V. E., M. V. Kabanov, Y. M. Andreev, V. G. Voevodin, P. P. Geiko, A. I. Gribenyukov and V. V. Zuev. (1988). "Applications of efficient parametric IR-laser frequency converters." Bulletin of the Academy of Sciences, USSR, Physical Series. **52** 87-92 Russian ref.: Izvestiya Akademii Nauk, SSSR, Physical Series **52** 1142-1148 (1988).